

## PATENT ABSTRACTS OF JAPAN

(11)Publication number : 07-235292

(43)Date of publication of application : 05.09.1995

---

(51)Int.Cl.            H01M 4/58    H01M 4/02    H01M 10/40

---

(21)Application number : 06-22284    (71)Applicant : MATSUSHITA

(22)Date of filing :            21.02.1994    (72)Inventor : KAZUHIRO OKAMURA  
   KAORU INOUE  
   JYUNNICHY YAMAURA

---

### CLAIMS

---

#### [Claim(s)]

[Claim 1] The nonaqueous rechargeable battery using cathode active material which consists of  $\text{Li}_x\text{NiO}_2$  ( $0 < x \leq 1$ ) coated with at least one sort  $\text{Li}_x\text{CoO}_2$  ( $0 < x \leq 1$ ) and  $\text{Li}_x\text{MnO}_2$  ( $0 < x \leq 1$ ).

---

### DETAILED DESCRIPTION

---

#### [Detailed Description of the Invention]

##### [The purpose of this invention]

To offer the nonaqueous rechargeable battery that has better cycleability and good life by control the reaction with electrolyte.

##### [Example]

##### [0014]

1.  $\text{LiNiO}_2$  was obtained by a well-known method.
2.  $\text{LiNiO}_2$  powder + water-soluble salt containing the transition metals (such as  $\text{Co}(\text{NO}_3)_2$  and  $\text{Mn}(\text{NO}_3)_2$ ) were mixed in aqueous solution.
3. The suspension + alkali salt (such as  $\text{LiOH}$ ) were mixed.  
So, we obtained  $\text{LiNiO}_2$  coated with the transition metals containing material.
4. The coated material was washed and dried.
5. The coated material + lithium hydroxide is heated for about 2 to 3 hours.

Spattering and mechanochemical coating are mentioned as other methods to obtain the coated material.

AQ